

Kisling AG Motorenstrasse 102 CH-8620 Wetzikon

Telefon +41 (0)58 272 01 01 Telefax +41 (0)58 272 01 03 info@kisling.com www.kisling.com

TECHNICAL DATA SHEET ergo.® 4280

Instant Gasket temperature resistant

Description

Very high viscous, fast sealing product for flanges in pumps, gear boxes......

This product shows high resistance against water, gas, LPG, oil and a wide range of technical chemicals, respectively solvents. It seals safely within the thermal range of –55°C up to +200°C and resists against impact and vibration. Certified acc. to **NSF ANSI 61** for use in commercial and residential potable water systems not exceeding 82°C. **NSF P1** listed for use in food processing areas.

Note: This is a regional approval. Please contact us for more information and clarification.

Physical Properties (liquid product)

Chemical Base: Diester of Methacrylic Acid

Colour: red / fluorescent

Viscosity at 25°C, Brookfield RVT

300.000 – 600.000 mPas spindle 7, 2,5 rpm

60.000 – 100.000 mPas spindle 7, 20 rpm

Density at 25°C: 1.05 g/cm³

Max. thread diameter: N/A
Max. gap filling: 0.50 mm

Flash point: > 100°C

Shelf life: 1 year at room temperature

Physical Properties (cured product)

Measured on M10 x 20 bolt - grade 8.8 black phosphatized - nut 0.8d (no on-torque)

Functional strength after: 3 - 6 hours

Final strength after: 6 - 12 hours

Loose-break torque: N/A

Prevailing torque: N/A

Tensile shear strength > 12 N/mm² DIN 54452

Tensile strength: > 10 N/mm² DIN 53288

Thermal range: - 55°C up to +200°C

WARRANTY INFORMATION - PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that KISLING products are safe, effective, and fully satisfactory for the intended end use. KISLING sole warranty is that the product will meet the KISLING sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. KISLING specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability. Unless KISLING provides you with a specific, duly signed endorsement of fitness for use, KISLING disclaims liability for any incidental or consequential damages. Suggestions of uses should not be taken as inducements to infringe any particular patent.